


SHEFFIELD ANALYTICAL SERVICES
A Division of Sheffield Assay Office

Unit D3, Cirrus Court
Aviation Business Park West
Bournemouth
Dorset
BH23 6BW



Order No.

Report No. 05015/02

Issued: 16/09/2015

Reprinted: 16/09/2015

Extract

Reference : QMTB16

Sample Date : 04/09/2015

Serial Number : 0046

Elution Test

Ni Elution

Element	Result
---------	--------

PiercingBar	<0.35 Pass
-------------	------------

TITANIUM INTERNAL

Elution results reported as $\mu\text{g}/\text{cm}^2/\text{week}$.

Based on BSEN1811:2011+A1:2015 (inc BSEN12472)

Piercing assemblies Pass = $<0.35 \mu\text{g}/\text{cm}^2/\text{week}$.

Other components Pass = $<0.88 \mu\text{g}/\text{cm}^2/\text{week}$.

Signature: Customer Services Coordinator - J Green

